

PHYSICAL TESTS

Combustion 30-62°C c. c. Naphtha ignited	No visual effect
24 h - Humidity @120°F, 96% +/- 2% RH	No visual effect
Belmar Scrape Adhesion, 4 Kg (ASTM 1297, ASTM D5178)	Pass
Hoffman Scratch Hardness Test, 800 g	Pass
Impact, 2 lbs bevel steel rod 8" drop	No cracks in film
Abrasion Resistance CS-17 wheels	900 cycles

NOTE: Testing excludes Kinon metal products. Metal products will behave as per their specific metal composition.